

**Klammertyp: Q aus rostbeständigem Edelstahl**

Drahtdurchmesser: 1,80mm  
Längen: 32-80mm  
Werkstoff: 1.4301



**Materialeigenschaften des Verbindungsmittels:**

Zugfestigkeit in Übereinstimmung mit EN 10088-1 mindestens 950 N/mm<sup>2</sup>

**Mechanische Eigenschaften des Verbindungsmittels:**

- Fließmoment (n. EN 14592):  $M_{y,k} = 970 \text{ Nmm}$
- Charakteristischer Ausziehparameter (EAD, 60°C, 75% rLf.):  $f_{ax,k} = 5,00 \text{ N/mm}^2$
- Charakteristischer Ausziehparameter (n. EN 14592):  $f_{ax,k} = 5,11 \text{ N/mm}^2$
- Charakteristischer Kopfdurchzug (n. EN 14592):  $f_{head,k} = 29,0 \text{ N/mm}^2$
- Bemessungswert der Tragfähigkeit (Lastwirkungsdauer)  $R_{ax,d} = 70 \text{ N}$

Werte gelten für Materialien mit einer charakteristischen Rohdichte  $p_k \geq 350 \text{ kg/m}^3$

**Brandverhalten** (n. 96/603/EG n. 200/605/EG) = Klasse **A1**

**Serviceklasse:**

Serviceklasse 3 in Übereinstimmung mit EN 1995-1



Mitglied im Fachverband  
Verbindungs- und Befestigungstechnik



# European Technical Assessment for staples as wood connecting fasteners

## ETA-16/0101



www.prebena.com

### Staples type: Q - stainless steel

Diameter: 1,80mm  
Length: 32-80mm  
Material: 1.4301



### Properties of the material used:

Tensile strength in accordance with EN 10088-1 min. 950 N/mm<sup>2</sup>

### Mechanical strength and stiffness:

- Yield Moment (acc. EN 14592):	$M_{y,k} =$	970 Nmm
- Withdrawl parameter (EAD, 60°C, 75% r. ah.):	$f_{ax,k} =$	5,00 N/mm <sup>2</sup>
- Withdrawl parameter (acc. EN 14592):	$f_{ax,k} =$	5,11 N/mm <sup>2</sup>
- Head pull-through parameter (acc. EN 14592):	$f_{head,k} =$	29,0 N/mm <sup>2</sup>
- Design value of resistance (Load duration)	$R_{ax,d} =$	70 N

Values are valid for materials with a characteristic density  $\rho_k \geq 350$  kg/m<sup>3</sup>

Reaction to fire (acc. 96/603/EG, acc. 200/605/EG) = Class A1

### Service class:

Service class 3 in accordance with EN 1995-1



Member of fasteners associations



Wilfried Bornemann GmbH & Co. KG

Seestraße 20 - 26 • 63679 Schotten • Germany

Phone: 0049 60 44 / 96 01 - 0 • Fax: 0049 60 44 / 96 01 • 820 - info@prebena.com • www.prebena.com